

Physical Properties			
Grade	Y.S. (Min)	T.S.(Min)	% Age Elongation on 5.65/So=Gl.
	Mpa	Mpa	
	(N/mm ²)	(N/mm ²)	
Fe 330	235	410	15%